

# Enabling Electric Aviation with Ultra High Energy Lithium Metal Batteries

John Lawson-PI (ARC), Tom Miller (GRC), James Wu (GRC), Bill Bennett (GRC), Charles Bauschlicher (ARC), Brianne Scheidegger (GRC), Justin Haskins (ARC)

NASA Aeronautics Research Mission Directorate (ARMD)

FY12 Seedling Phase I Technical Seminar

July 9-11, 2013



#### **Electric Aviation**

- Green aviation: high efficiency, low emissions, low noise
- Solar Impulse: largest technological limitation -- battery storage
- Hybrid aircraft: battery weight is significant limitation
- Commercial aircraft: battery powered onboard systems
- Boeing 787 Dreamliner: current battery electrolytes are flammable
- Progress in electric aviation will depend on advances in <u>ultra high</u> <u>energy</u>, <u>safe</u> batteries









#### Lithium Metal Anodes

#### NASA Aeronautics Research Institute





Battery failure due to dendrites


F. Orsini et al., J. Power Sources 76, 19-29 (1998)

- Potential for 5X increase in storage capacity
- Safety and cycling problems: issues for Li-Air, Li-S, etc
- Holy Grail of advanced battery technology



### Ionic Liquid Electrolytes

NASA Aeronautics Research Institute



Two Ionic Liquids are similar but have very different cycling behavior - why?

Fundamental understanding will enable design of ultra high energy batteries



## Seedling Phase I Project


- Innovation: computational predictive <u>tool</u> tightly coupled to experiments to accelerate fundamental understanding, screening and design of novel electrolytes for advanced batteries
- Application: investigate <u>two</u> Ionic Liquid electrolytes (one good cycling and one poor) for Lithium metal anode batteries
- Cross-Center, Multi-Disciplinary Team
- ARC Computational Materials Group: modern computational material science methods
- **GRC Electrochemistry Branch:** wide-ranging experience in battery development experimental characterization
- Benefit/Impact: predictive tool for accelerated development of ultra high energy, safe batteries
- Aggressive Work Plan (12 milestones) -- all met or exceeded



### **Technical Approach**

NASA Aeronautics Research Institute


#### I. Isolated Ionic Liquids






- Transport simulations
- Experimental validation


#### II. Experimental Cell Characterization





- Build cells
- Electrochemical characterization
- Surface layer identification

#### III. Ionic Liquid-Electrode interface



- Interface simulations with voltage
- Electric double layer structure

#### IV. Interfacial chemistry



- Electrolyte surface decomposition
- Chemical pathways
- Surface layer formation



## Phase I Seedling

- I. Isolated Ionic Liquids
- II. Experimental Cell Characterization
- III. Ionic Liquid-Electrode Interfaces
- IV. Interfacial Chemistry
- V. Summary/Future Directions



### Molecular Dynamics Simulations

NASA Aeronautics Research Institute

Newton's law F=ma for atoms

$$F = -\nabla E$$

Bonded interactions:

$$E^{bond} + E^{angle} + E^{torsion}$$

Non-bonded interactions:


$$E^{vdw} + E^{qq}$$

"Polarizable" interactions

$$E^{\mu q} + E^{\mu \mu}$$

- New polarizable software module for lonic Liquid simulations developed
- Massive datasets for analysis

[pyr14][TFSI]





### Thermodynamics

NASA Aeronautics Research Institute

Well-established theoretical foundation (statistical mechanics)

**Heat Capacity** 

$$C_{P} = \frac{\P(H + PV)}{\P T} \bigg|_{P} = \frac{\left\langle \mathcal{O}(H + PV)^{2} \right\rangle_{NPT}}{k_{B}T^{2}}$$

**Isothermal Compressibility** 

$$D_T = \frac{1}{V} \frac{\P V}{\P P} \bigg|_{T} = \frac{\left\langle OV^2 \right\rangle_{NPT}}{\left\langle V \right\rangle k_B T}$$

Thermal Expansion Coefficient

$$\partial_{P} = \frac{1}{V} \frac{\P V}{\P T} \bigg|_{P} = \frac{\left\langle dV d (H + PV) \right\rangle_{NPT}}{\left\langle V \right\rangle k_{B} T^{2}}$$

Thermal Pressure Coefficient

$$g_V = \frac{\P P}{\P T} \bigg|_V = \frac{\partial_P}{\partial_T}$$



#### **Transport Properties**

NASA Aeronautics Research Institute

Non-equilibrium transport coefficients (fluctuation-dissipation theorems)

Diffusion

$$D \mid 0 dt \langle v(t)v(0) \rangle$$

Viscosity

$$h_{xy} \perp \hat{0} dt \langle p_{xy}(t) p_{xy}(0) \rangle$$


**Ionic Conductivity** 

$$g_{IC} \sqcup \frac{d}{dt} \langle (qr(t) - qr(0))^2 \rangle$$




### Example: Li<sup>+</sup> Ion Solvation Shell

#### NASA Aeronautics Research Institute




Detailed molecular structure





Anion distribution about Li ions







#### Density

NASA Aeronautics Research Institute

#### Neat Ionic Liquids



#### Lithiated Ionic Liquids




Excellent agreement with GRC experiments




#### Viscosity

NASA Aeronautics Research Institute

[pyr14][TFSI]



 $[EMIM][BF_4]$ 





Good agreement with GRC results



#### Diffusion coefficient

NASA Aeronautics Research Institute






Diffusion data from GRC in progress



#### **Ionic Conductivity**

NASA Aeronautics Research Institute



Good agreement with GRC results

**Conclusion**: good agreement on broad range of electrolyte properties





## Phase I Seedling

- I. Isolated Ionic Liquids
- II. Experimental Cell Characterization
- III. Ionic Liquid-Electrode Interfaces
- IV. Interfacial Chemistry
- V. Summary/Future Directions



#### Lithium Coin Cell







- Laboratory cells easily constructed
- Focus characterization of the Li metal electrode



# Cell Cycling






- [EMIM][BF<sub>4</sub>] cell fails after <u>150</u> cycles
- [pyr14][TFSI] cell cycles successful up to **1750** cycles



## Impedance Spectroscopy




- [EMIM][BF<sub>4</sub>] cell has *increasing* resistance
- [pyr14][TFSI] cell has *decreasing* resistance (increasing Li surface area)



## Cyclic Voltammetry

- [pyr14][TFSI] cell: Li plating/stripping
- [EMIM][BF<sub>4</sub>] cell: no Li stripping
- [EMIM][BF<sub>4</sub>] cell: decomposition
- Consistent with impedance data
- [EMIM][BF<sub>4</sub>] cell with VC additive improves Li plating/stripping
- Decomposition explored in Phase II
- Additives to be explored in Phase II






## Surface Morphology: [pyr14][TFSI]

NASA Aeronautics Research Institute

- Li electrode after 1780 cycles
- "Mossy" Li deposits rich in electrolyte elements (O, S, F)
- Smooth Li surface visible where mossy layer flaked off
- Mossy layer source of increased surface area
- Consistent with reduction in impedance




Conductive mossy surface layer facilitates good cycling



# Surface Morphology: [EMIM][BF<sub>4</sub>]

NASA Aeronautics Research Institute

- Li electrode after 130 cycles
- "Waxy" film covers ~75% of Li surface (rich in F and C)
- Film consists of electrolyte decomposition products
- Li under film appears bright and un-utilized
- Reduction in active area
- Consistent with increase in impedance



Insulating waxy surface layer results in poor cycling

Fundamental question: Why does one electrolyte give favorable surface layer and the other does not?



## Phase I Seedling


- I. Isolated Ionic Liquids
- II. Experimental Cell Characterization
- III. Ionic Liquid-Electrode Interfaces
- IV. Interfacial Chemistry
- V. Summary/Future Directions



### Electrolyte-Electrode Interface

NASA Aeronautics Research Institute


**Question:** How does Ionic Liquid organize itself at electrode interface?




- Interface simulations with applied voltage (not milestone)
- Produced new (second) software module to be distributed
- <u>Full</u> interface properties as function of voltage in Phase II



# Electric Double Layer: [pyr14][TFSI]








### Ion Density: [pyr14][TFSI]

NASA Aeronautics Research Institute



- Molecular layering near interface
- Classical theory predicts exponential decay

**Conclusion:** Molecular ordering near interface sets stage for interfacial reactions



## Phase I Seedling

- I. Isolated Ionic Liquids
- II. Experimental Cell Characterization
- III. Ionic Liquid-Electrode Interfaces
- **IV.** Interfacial Chemistry
- V. Summary/Future Directions




## Surface Reactions: [EMIM][BF<sub>4</sub>]

NASA Aeronautics Research Institute

**Question:** What are the chemical reactions and products between Li electrode and Ionic Liquid electrolyte?

#### Ab Initio Molecular Dynamics

- High fidelity modeling
- Zero voltage
- Ions bound to surface
- No decomposition of ions



BF<sub>4</sub> anion

Lithium slab

EMIM cation



## Surface Reactions: [pyr14][TSFI]


NASA Aeronautics Research Institute

#### **Ab Initio Molecular Dynamics**

- High fidelity modeling
- Zero voltage
- Ions bound to surface
- Immediate decomposition of TSFI anion
- Screening tool for electrolytes(?)

**Conclusion:** At zero voltage, very different anion decomposition behavior and products. Suggests that different surface layers will result (preliminary).

Phase II will consider surface reactions with applied voltage



TFSI anion

Lithium slab

pyr14 cation



## Phase I Seedling

- I. Isolated Ionic Liquids
- II. Ionic Liquid-Electrode Interfaces
- III. Interfacial Chemistry
- IV. Experimental Cell Characterization
- V. Summary/Future Directions



### Summary

#### NASA Aeronautics Research Institute


#### Phase I Major Accomplishments:

- Determined transport properties (computation/experiment) of two ILs
- Built and characterized Li cells (cycling, impedance, voltammetry, SEM/EDAX)
- Identified different surface layers for different electrolytes
- Determined interface double layer properties (computation)
- Identified initial surface reactions from simulations (computation)
- Cross-Center, Multi-Disciplinary Team: ARC/GRC
- Benefit/Impact: predictive tool tightly coupled to experiment for accelerated development of ultra high energy, safe batteries
- Milestones: We have met or exceeded all 12 milestones
- Products: two software modules to be distributed to community
- Dissemination: 3-4 journal articles plus conference presentations
- Interest in Our Work: DOE/ORNL, ARL, IBM Almaden Research
- Spin-off Applications: Ionic Liquids for Tribology, EPSCoR proposal




#### **Future Directions**

#### NASA Aeronautics Research Institute



- Full interfacial properties vs voltage
- Measure interface capacitance
- Surface reactions vs voltage
- Compare to CV data
- Surface layer formation simulations
- Compare to SEM/EDAX data
- Additives and alternative ILs
- Modeling support of optimization

V. Full Cells: Cathode and Anode



- Build and characterize full cells
- Optional: Li-Air cell with IL electrolyte
- **Optional:** Oxidative stability modeling



### Seedling Team

- GRC Electrochemistry Team
  - Bill Bennett
  - James Wu
  - Tom Miller
  - Brianne Scheidegger
- ARC Computational Modeling Team
  - John Lawson
  - Justin Haskins
  - Charlie Bauschlicher
  - Josh Monk
  - Eric Bucholz
- External Collaborators
  - Oleg Borodin (ARL)
  - P. Ganesh (ORNL)
  - Prof. Farideh Jalilehvand (Univ of Calgary)
  - Prof. Mohsen Zaeem (Missouri Univ S&T)



## Thank you for funding!